



P4615A90

MOLYTHANE

TYPICAL PHYSICAL PROPERTIES

HARDNESS, SHORE A	95
MODULUS @ 100% ELONGATION, psi	2058
MODULUS @ 300% ELONGATION, psi	4646
ULTIMATE TENSILE STRENGTH, psi	8046
ULTIMATE ELONGATION, %	485
SPECIFIC GRAVITY	1.20
REBOUND RESILIENCE, %	37
COMPRESSION SET 70 hrs @ 158°F, %	34.2
TEMPERATURE RANGE	-65° TO +200° F

NOTE: THESE ARE TYPICAL VALUES AND SHOULD
NOT BE USED AS SPECIFICATION LIMITS

Compound P4615A90

Test Results

Media	Hardness Change, Pnts.	100% Modulus Change, %	Ultimate Tensile Change, %	Elongation Change, %	Weight Change, %	Volume Change, %
Original	96	1843	7596	526	-	-
Fuel A	-1	-4	+12	+3	+1	+1
Final Value	95	1774	8523	541		
Fuel B	-3	-24	-20	-5	+9	+12
Final Value	93	1405	6105	502		
Fuel C	-3	-27	-28	-7	+13	+18
Final Value	93	1341	5482	491		
Methanol	-5	-41	-42	-4	+9	+13
Final Value	91	1083	4425	503		
JP-4 Jet Fuel	-1	-14	+2	-5	+3	+4
Final Value	95	1581	7718	501		
JA Jet Fuel	-1	-11	+8	-3	+2	+2
Final Value	95	1641	8187	510		
ASTM #1 Oil	-1	-9	+22	+23	0	0
Final Value	95	1686	9302	647		
IRM 903	-1	-12	+15	+21	+6	+7
Final Value	95	1623	8747	637		
MIL-H-5606	-1	-13	+2	+15	+4	+6
Final Value	95	1597	7715	605		
Jet Oil II	-1	-10	+9	+8	+8	+9
Final Value	95	1661	8250	570		
Stauffer 7700	-2	-14	+4	+14	+7	+8
Final Value	94	1590	7879	600		
Rando HD32	-1	-5	+24	+10	+1	+1
Final Value	95	1759	9404	579		
Rapeseed Oil	-1	-10	+3	+31	+1	+1
Final Value	95	1663	7791	689		
Distilled Water	-2	-29	-31	+52	+1	+2
Final Value	94	1310	5248	799		
Oven Air Age	-1	-5	+21	+17	0	0
Final Value	95	1750	9182	616		
Ethylene Glycol	-4	-32	-28	+59	+5	+6
Final Value	92	1255	5450	834		

LL-1093



70 Hrs @ Room Temperature



168 Hrs @ 100° C

Warning! Failure, improper selection or improper use of the product and/systems described herein of related items can cause death, personal injury or property damage. This document and other information from Parker Hannifin Corporation, its subsidiaries and authorized distributors provide product and/or system options for further investigation by user having technical expertise. It is important that you analyze all aspects of your application and review the information concerning the product or system in the current Product catalog. Due to the variety of operating conditions and applications for these products or systems, the user, through his own analysis and testing is solely responsible for making the final selection of the product and systems and assuring that all performance, safety and warning requirements of the application.